

Cable Corrosion Protection

Standard Specification for Cable Stay Bridges

SECTION I – General

The material covered by this specification shall be an elastomeric cable wrap that meets the following requirements:

1. It is colorfast without applying paint.
2. It is applied in a spirally wound manner over the bridge cable with a 50 percent overlap creating the appearance of a smooth finish.
3. It is heated in place to fuse the seams of the overlapped wrap and to shrink the wrap snug against the underlying cable.
4. It is applied under tension with an automatic wrapping device as described in Section III.
5. It is BABA (Build America, Buy America) compliant
6. It is self-extinguishing after exposure to flame.

The elastomeric cable wrap system that is covered by this specification is the subject of a patent issued in the U.S. and various foreign countries. The material covered by this specification can be acquired from:

The D.S. Brown Company
 300 East Cherry Street
 North Baltimore, Ohio 45872
 Phone: (419) 257-3561 Fax: (419) 257-2200

SECTION II – Materials and Physical Properties

Elastomeric Wrap

The wrap is based on a cross-linking chlorosulfonated polyethylene polymer. Wrap systems based on thermoplastic materials, polychloroprene polymers, other natural or synthetic polymers or plastics will not be allowed.

The wrap shall be a three-ply laminated construction. The required thickness of the wrap is 45 mils, ± 3 mils, so that after applying the wrap on the bridge cable at a 50 percent overlap, its total thickness is approximately 90 mils.

Physical Properties – Wrap

Membrane Breaking Strength (ASTM D751)	110 pounds
Membrane Elongation @ Break % (ASTM D751)	120% minimum
Tear Propagation (ASTM D751 tongue tear)	15 pounds
Bonded Seam Strength, Shear (ASTM D751 2" min)	140 pounds
Bonded Seam Strength, Peel	30 pounds
Hydrostatic Resistance (ASTM D751)	80 psi
Puncture Resistance (FTMS 101B method 2031)	70 pounds
Low Temperature Bend (ASTM D2136 @ -40°C)	No cracks
Ozone Resistance (ASTM 1149)	No cracks
Shore A Hardness (ASTM D2240)	85 ± 5

When specified, clamping straps shall be stainless steel. The straps shall be a minimum of 0.025 inches (0.60 mm) thick and 0.375 inches (9.50 mm) wide.

SECTION III – Installation

The elastomeric cable wrap shall be applied by an automatic wrapping device applying enough tension to slightly stretch the wrap. The wrapping device shall be capable of maintaining a constant angle of application. Within 24 hours of wrapping the cable, the elastomeric wrap shall be heated to achieve fusion of the overlapped seams and shrinkage of the wrap against the underlying cable. The heating shall be with an electric heating blanket capable of generating and sustaining temperatures of 270°F. Clamping devices that are integrally incorporated in the blanket shall keep the blanket in intimate contact with the elastomeric wrap on the surface of the cable. Blanket temperature shall be maintained by the use of a controller in conjunction with a thermocouple which is integral to the blanket. An experienced technician who is employed by the manufacturer shall assist the installation crew during the startup of the wrapping and heating process.



SECTION IV – Payment

Payment for the elastomeric cable wrap shall be lump sum and shall include the wrap itself and all incidental materials necessary for the installation including stainless steel clamps, automatic wrapping device, heating blanket, blanket controller and miscellaneous materials.